

**FEATURES:**

Resirene 2210 is a HIPS grade suitable for injection molding processes

- High Impact
- High Flow
- FDA: 21 CFR 177.1640
- High Productivity
- Easy processing

**APPLICATIONS:**

Thin wall devices, intricate molds, yogurt cups, toys, MB basis

**PROPERTIES**

PHYSICAL	English	Value	Metric	Value	METHOD
<b>Melt Flow Rate (200 °C/5.0Kg)</b>	<b>g/10 min</b>	<b>16.20</b>	<b>g/10 min</b>	<b>16.20</b>	ASTM D1238
<b>Specific Gravity</b>	<b>lb/in<sup>3</sup></b>	<b>0.04</b>	<b>g/cm<sup>3</sup></b>	<b>1.05</b>	ISO 1183
<b>MECHANICAL</b>					
<b>Break Elongation</b>	<b>%</b>	<b>60</b>	<b>%</b>	<b>60.0</b>	ASTM D638
<b>Tensile Modulus</b>	<b>psi</b>	<b>242,313</b>	<b>MPa</b>	<b>1,670.7</b>	ASTM D638
<b>IMPACT</b>					
<b>Notched Izod Impact (0.50 in)</b>	<b>ft-lbf/in</b>	<b>1.80</b>	<b>J/m</b>	<b>96</b>	ASTM D256
<b>THERMAL</b>					
<b>Vicat Temperature</b>	<b>°F</b>	<b>172</b>	<b>°C</b>	<b>78</b>	ASTM D1525
<b>HDT @ 264 psi (unannealed)</b>	<b>°F</b>	<b>156</b>	<b>°C</b>	<b>69</b>	ASTM D648

Typical values represent average laboratory values and are intended as guides only, not as specific specification limits. Properties designated in this standar have been determined in accordance with the current issue of the specified testing methods.

**INJECTION MOLDING CONDITIONS**

	<b>°C</b>	<b>°F</b>
Profile	200-230	392-446
Maximum Recommended	240	464

**ADDITIONAL INFORMATION**

**WARNING:**

Combustion of this material may cause hazardous fumes and gases that may be dangerous to one's health, especially in enclosed places. It should be noted that excessive heating or long residence times may cause degradation or yellowing.

**NOTE:**

The data contained herein is provided for information purposes only. By providing such information, Resirene, S.A. de C.V. makes no guarantee and does not assume any liability with respect to the accuracy or completeness of such information and the results obtained with this product in any specific instance; and hereby expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be construed as a license to use the products of Resirene, S.A. de C.V. in any manner that would infringe any patent.

**Resirene S.A. de C.V.**

Km 15.5 carret. Fed. Puebla-Tlaxcala  
90780 Xicohtzinco, Tlaxcala, MEX  
MEX toll free 01 800 RESINAS  
USA toll free 1 866 372 3470

visit us at [resirene.com](http://resirene.com)