



**PREMIER**  
POLYMERS, LLC.

## Premier PH030

### Homopolymer Polypropylene

**MELT FLOW: 2.8**

**DENSITY: 0.9**

**Premier PH030** is a homopolymer polypropylene with easy processing performance designed for oriented film, including metallizable film.

<u>Resin Property</u>	<u>Typical Value</u>	<u>Units</u>	<u>Test Method</u>
Melt Flow Rate, I <sub>2</sub> @ 230 °C	2.8	g/10 min	ASTM D-1238
Density	0.9	g/cm <sup>3</sup>	ASTM D-1505
Tensile Strength at Yield (2.0 in/min; 51mm/min)	4,930 (34.0)	Psi (MPa)	ASTM D-638
Flexural Modulus, 1% Secant (0.051 in/min; 1.3mm/min)	208,000 (1,430)	Psi (MPa)	ASTM D-790A
Flexural Modulus, 1% Secant (0.51in/min; 13mm/min)	232,000 (1,600)	Psi (MPa)	ASTM D-790A
Elongation at Yield (2.0 in/min; 51mm/min)	10	%	ASTM D-638
Notched Izod Impact Strength @ 73°F (23°C)	0.97 (52)	Ft-lb/in (J/m)	ASTM D-256A
Deflection Temperature Under Load (66 psi – Unannealed)	191 (88.3)	°F (°C)	ASTM D-648

Premier Polymers cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties but they should not be used to establish specification limits or used alone as the basis of design.

Premier Polymers, LLC. 16800 Imperial Valley Drive, Suite 400 Houston, TX 77060  
Phone: 281-902-0900 Fax: 281-260-8096