

Paxon™ AA45-004

High Density Polyethylene Resin

Product Description

AA45-004 is a blow molding high density polyethylene copolymer offering exceptional stress cracking resistance and impact performance.

General

Availability ¹	<ul style="list-style-type: none"> Latin America North America
Additive	<ul style="list-style-type: none"> Thermal Stabilizer: Yes Antistatic: No
Applications	<ul style="list-style-type: none"> Agriculture Products Containers Food packaging Household and Industrial chemical containers Pharmaceutical Packaging
Revision Date	<ul style="list-style-type: none"> 03/01/2010

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.945 g/cm ³	0.945 g/cm ³	ASTM D4883
Melt Index (190°C/2.16 kg)	0.35 g/10 min	0.35 g/10 min	ASTM D1238

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Brittleness Temperature	< -105 °F	< -76 °C	ASTM D746
Vicat Softening Temperature	250 °F	121 °C	ASTM D1525

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	3500 psi	24 MPa	ASTM D638
Flexural Modulus	150000 psi	1000 MPa	ASTM D790
Environmental Stress-Crack Resistance 100% Igepal	> 1000 hr	> 1000 hr	ASTM D1693

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Impact Strength	110 ft-lb/in ²	230 kJ/m ²	ASTM D1822

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

1. Values are typical and should not be interpreted as specifications. Values may change with future development. 2. All molded properties were measured on compression molded plaques. 3. Flexural modulus tested using Procedure A (1"x3"x0.125"), Tangent calculation. 4. ESCR tested using Condition B, 100% Igepal. 5. AA45-004 has NSF and UL recognition. Contact your ExxonMobil Chemical representative for details.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Paxon™ AA45-004
High Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2016 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com